



BALDOCK
The Barn, 35 Whitehorse St
Baldock, Herts
SG7 6QF
Tel: 07714 245566
Email: lbritton@silvion.co.uk
Web: www.silvion.co.uk

GRANTHAM
The Brambles, Grantham Rd
Old Somerby, Grantham
Lines, NG33 4AB
Tel: 07872 857310
Email: rbritton@silvion.co.uk
Web: www.silvion.co.uk

TYPE SW200 Ag/AgCl 0.5M KCl PERMANENT SEAWATER & BRACKISH WATER REFERENCE ELECTRODE



The silver/silver chloride (Ag/AgCl) elements in all Silvion electrodes are manufactured using a “unique” and advanced technique that results in a porous silver matrix. The matrix is then coated with precise quantities of silver chloride to ensure:

- 1). HIGH RELIABILITY;
- 2). HIGH STABILITY;
- 3). GREATER ACCURACY;
- 4). INCREASED LIFE PERFORMANCE.

NOTE:

The SW200 electrode has an internal electrolyte of 0.5M KCl making it the ideal choice for use in seabed sand, seabed mud and estuary mud and waters.

The SW200 is fitted with a perforated cap to protect the ceramic frit sensing head from mechanical damage.

SILVION REFERENCE ELECTRODES

>40 Years' Service to the Corrosion Prevention Industry

Registered Office: Windsor House, A1 Business Park at Long Bennington, Nottinghamshire NG23 5JR
Registered in England No: 6860239 VAT No: 975 9426 61 EORI No: GB975942661000



BALDOCK
The Barn, 35 Whitehorse St
Baldock, Herts
SG7 6QF
Tel: 07714 245566
Email: lbritton@silvion.co.uk
Web: www.silvion.co.uk

GRANTHAM
The Brambles, Grantham Rd
Old Somerby, Grantham
Lincs, NG33 4AB
Tel: 07872 857310
Email: rbritton@silvion.co.uk
Web: www.silvion.co.uk

OUTER CASING

MATERIALS.....	Acetal body with porous ceramic sintered disc and nylon spiral cable gland
DIMENSIONS.....	Length: 234mm (300mm w/ gland); Diameter: Body: 22mm; Weight: 30mm
CERAMIC DISC DIAMETER.....	35mm
WEIGHT (W/O CABLE).....	300g

SILVER CHLORIDE ELEMENT

MATERIALS.....	Silver compounds are 99.90% pure
DIMENSIONS.....	Length: 50mm (+/- 2mm); Section: 5mm x 5mm
SURFACE AREA.....	Geometric: 10cm ² ; Real: 500cm ²

ELECTROLYTE	Inert electrolyte with 0.5 Molar KCl
--------------------------	--------------------------------------

PERFORMANCE DATA (See N.B. below for details)

Vs STANDARD HYDROGEN ELECTRODE @25°C.....	+250mV
IUPAC* GUIDELINES IN 0.5M KCL SOLUTION Vs SCE @ 25°C	+9mV
HISTORIC DNV GUIDELINES IN 0.5M KCL SOLUTION Vs SCE @20°C.	-5mV
ACCURACY.....	+/-5mV
STABILITY (POTENTIAL DRIFT AT CONSTANT TEMP AND ENVIRONMENT)....	+/- 1mV (24 Hrs) @ 5µA load
TEMP COEFFICIENT.....	-0.65mV/°C
Vs STANDARD HYDROGEN ELECTRODE @25°C.....	+250mV
INTERNAL RESISTANCE.....	Less than 500 Ohms
THEORETICAL DESIGN LIFE	30 years @ 0.1µA load

QA/QC

All our electrodes are fully tested, calibrated and supplied complete with a calibration certificate. They are individually identified with a unique serial number to ensure full traceability. All dimensions +/-1mm unless otherwise stated.

WARRANTY

Our reference electrodes are fully warranted against defects in materials and workmanship for six months from the date of receipt. We will replace/ refund any defect units within this period, but we require the unit(s) for examination to determine any fault.

N.B. Under no circumstances should the reference electrode be connected directly to the structure or the electrode will self-discharge and cease to operate. The minimum input impedance for the voltmeter used to measure the structure to electrolyte potential should be 10 MOhm.

In published literature, potential values for common reference electrodes used in Corrosion are measured with respect to a Standard Hydrogen Electrode (SHE) at 25°C and are shown as a positive value. However, historical DNV guidelines have required Ag/AgCl electrodes to have a potential within the range of -5mV +/- 5mV against a Saturated Calomel Electrode (SCE) at ambient temperatures in seawater (or 3% (0.5M) to 3.5% (0.546M) NaCl or KCl solutions). The DNV guidelines had been based on the value measured when the SCE electrode is connected to the positive terminal of the voltmeter and the Ag/AgCl electrode connected to the negative terminal. Silvion Ltd quote reference electrode potential values in this data sheet using both the electrode connection arrangement originally adopted by DNV giving a negative potential measurement and currently used by *International Union of Pure and Applied Chemistry (IUPAC) which gives a positive potential measurement. It should be noted that the polarity of the reference electrode connection affects the polarity of the potential measurement that is obtained, but not its magnitude.

The information provided in this document was accurate at the time it was published; however, we reserve the right to revise this document without prior warning.

SILVION REFERENCE ELECTRODES

>40 Years' Service to the Corrosion Prevention Industry

Registered Office: Windsor House, A1 Business Park at Long Bennington, Nottinghamshire NG23 5JR

Registered in England No: 6860239 VAT No: 975 9426 61 EORI No: GB975942661000